

INTERNATIONAL CENTRE FOR AUTOMOTIVE TECHNOLOGY

[A Division of NATRIP Implementation Society (NATIS), Govt. of India]

NON TRANSFERABLE

TEST REPORT

C T O B L 5055

Date: 30.11.2016



- 1.0 NAME AND ADDRESS OF THE CUSTOMER : M/s. Polyhose India(Rubber) Pvt. Ltd.
Plot No. F37-F42 & F50-F55, SIPCOT Industrial Park,
Irrungattukottai, Pennalur Post, Sriperumpudur
Taluk- 602117, Tamil Nadu, India
- 2.0 CUSTOMER LETTER REF. : CCTNPOIPLCEL47745 Dated 15-Oct-2016
- 3.0 DESCRIPTION OF COMPONENT :

1	Name of the component	LPG hose assembly
2	Name and address of the manufacturer	Same as Sr. No. 1.0
3	Dimensions of the component	Nominal Size =12mm, Bore Size = 13.2 mm, Outer Diameter = 22.7 mm
4	Drawing No.	PHIR-001-02
5	Markings	POLYHOSE LOGO LPG HOSE NB 12.0mm(1/2") Max W.P. 2.5MPa as per IS 9573:2012 for Type I

- 4.0 TEST OBJECTIVE :
To evaluate performance of LPG hose assembly as per the requirements given in IS 9573:2012 as amended up to date.

- 5.0 TEST REQUIREMENTS, OBSERVATIONS AND RESULTS:
Please refer test requirements/results in Annexure-I of the report.

- 6.0 CONCLUSION:
LPG hose assembly submitted by M/s. Polyhose India (Rubber) Pvt. Ltd. specified in Sr. no. 3.0 of this test report meets the requirements of all the tests as per IS 9573:2012 as amended up to date.




Prepared By	Checked By		Approved By	
UDIT KAUL	MAHENDAR PAL		PAMELA TIKKU	
Asst. Manager	Sr. Manager		Sr. General Manager	

Page
1 of 4
+
Drawing
(47745)

DISCLAIMER




1. ICAT issues Test reports/ Extension reports/ Developmental Reports for vehicles/ parts/ components/ assemblies etc. based on the documents produced and/or prototype / vehicle(s) or sample(s) submitted by the applicant and testing thereof.
2. ICAT issues Test reports/ Extension reports/ Developmental Reports in compliance to Motor Vehicle Act/ Central Motor Vehicle Rules and their provisions as amended from time to time or any other statutory orders under which ICAT is authorized. Other Rules/Acts are outside the purview/scope of the Test reports/Extension reports/ Developmental test reports
3. Test(s) on prototype/ vehicle(s)/ sample(s) is/are carried out on the basis of standard procedures as notified under specific rules/ requested by the applicant. Results of such tests are property of bearer of Test Reports/ Extension Reports / Developmental test reports. These results cannot be disclosed unless specifically so ordered by Government, Court, etc
4. Unless otherwise supported by a separate Certificate, this Test report Extension Reports / Developmental test reports shall not be considered in isolation as valid Type approval for any vehicle
5. ICAT is not responsible for testing each vehicles/ parts/assemblies etc. for which Test Reports/ Extension reports/ Developmental test reports is issued. Further, ICAT is not responsible for ensuring manufacturing quality of the vehicles/ components/ parts/ assemblies etc. for which the Test Reports/ Extension reports/ Developmental test reports is /are issued.
6. ICAT is no way responsible for any misuse or copying any design/type/system in connection with entire vehicle/ components/parts and assemblies covered under the Test Reports/ Extension reports/ Developmental test reports is /are issued
7. Breach of any statutory provisions, of Indian laws or laws of other countries, will be sole responsibility of the customer. ICAT shall not be liable for any claims or damages made by the customer, whatsoever. The customer shall alone be liable for the same and undertakes to indemnify ICAT in this regard
8. Further, ICAT has the right, but not under obligation to initiate cancellation / withdrawal of the Test report/Extension/ Developmental test report is/are issued, in case of any fraud, misrepresentation, when it surfaces and comes in the knowledge of ICAT
9. No extract, abridgment or abstraction from this test report may be published or used to advertise the product without the written consent of the Director, ICAT, who reserves the absolute right to agree or reject all or any of the details of any items of publicity for which consent may be sought

The appropriate local court at Gurgaon shall have the jurisdiction in respect of any dispute, claim or liability arising out of this report.




Prepared By		Checked By	Page 2 of 4 + Drawing (47745)
			
UDIT KAUL		MAHENDAR PAL	
Asst. Manager		Sr. Manager	

Annexure I

Sr No	Test	Test Requirements	Observations / Results
1	Dimensions and Material test (Cl. No. 5.2 and 5.3)	Perform the dimensions and tolerance measurements as per Cl. No. 5.3. Verify material requirements as per Cl. No. 5.2.	All the Dimensions and tolerances are within acceptable limits. Satisfactory
2	Adhesion Test (Cl. No. 5.5.1 of IS 9573:2012)	The minimum adhesion between reinforcement and cover shall not be less than 1.5 kN/m.	Cover to reinforcement = 2.2 kN/m. Satisfactory
3	Low Temperature Flexibility Test (Cl. No. 5.5.2 of IS 9573:2012)	When a cut test piece is conditioned at $-40 \pm 2^\circ\text{C}$ for 5h and then bent to 180° around a mandrel with 12 times the nominal bore diameter; no cracks or breakage shall be shown.	After 5 h exposure to -40°C , No crack was observed when the hose was bent through 180° around the mandrel. Satisfactory
4	Flexibility of the hose (Cl. No. 5.5.3 of IS 9573:2012)	The hose shall be capable of being bent to the radius given in Table 1 of IS 9573:2012 flatness shall not exceed 10% of the outside diameter.	No structural damage was observed when the hose was bent through radius of 95mm. Satisfactory
5	Ozone Resistance Test (Cl. No. 5.5.4 of IS 9573:2012)	When Pieces of lining and cover are exposed to ozone environment of 50 ppm at $40 \pm 2^\circ\text{C}$ for 72 ± 2 h, pieces shall not show any signs of cracking under 2X magnification.	No cracks observed on the sample of cover and lining when subjected to ozone environment under stress condition. Satisfactory
6	Proof Pressure Test (Cl. No. 5.5.5.1 of IS 9573:2012)	A complete Hose assembly when subjected to internal hydraulic pressure equal to 5.0 MPa for 1 min, the change in the length shall be within the range of 12% of its original length.	No change in original length observed when the hose in subjected to 5 Mpa hydraulic pressure. Satisfactory
7	Bursting Pressure Test (Cl. No. 5.5.5.2 of IS 9573:2012)	Representative Samples of hose shall not burst below 10 MPa when subjected to internal hydraulic pressure.	Burst observed at 206.84 bar (20.68MPa) hydraulic pressure. Satisfactory

Prepared By		Checked By	Page 3 of 4 + Drawing (47745)
			
UDIT KAUL Asst. Manager		MAHENDAR PAL Sr. Manager	

Sr No	Test	Test Requirements		Observations / Results	
8	Tensile Strength and Elongation at break of Lining and Cover of the Hose (CI No. 5.4.1 of IS 9573:2012)	Lining	Cover	Lining	Cover
		Tensile Strength = 10.0 MPa(min)	Tensile Strength = 10.0 MPa(min)	Tensile Strength = 18.21 MPa(min)	Tensile Strength = 16.32 MPa(min)
		Elongation = Min 200 %	Elongation = Min 250 %	Elongation = Min 238 %	Elongation = Min 298 %
9	Acceleration Aging Test (CI No. 5.4.2 of IS 9573:2012)	Lining	Cover	Lining	Cover
		Tensile Strength = -25%	Tensile Strength = -50%	Tensile Strength = -12%	Tensile Strength = -23%
		Elongation = -50 %	Elongation = -50 %	Elongation = -17 %	Elongation = -28 %
10	Resistance to n-Pentane (CI No. 5.4.3 of IS 9573:2012)	1) % n-pentane absorbed should be less than 10% of initial mass of the lining. 2) % n-pentane extra should be less than 5% of initial mass of the lining.		% n-pentane absorbed = +2.12% % n-pentane absorbed = +2.3% Satisfactory	
11	Electrical Continuity test (CI No. 5.5.6 of IS 9573:2012)	The electrical continuity of wires in textile reinforced Type I hose after subjecting it to proof pressure test as per 5.5.5.1 shall be tested and maintained for each hose length from one end to another.		Beaded wire in the hose shows end to end continuity. Satisfactory	
12	Grip Strength test (CI No. 5.5.7 of IS 9573:2012)	When Pieces of lining and cover are exposed to ozone environment of 50 ppm at 40 + 2°C for 72+ 2h, pieces shall not show any signs of cracking under 2X magnification.		Not Applicable	
13	Burning test (CI No. 5.5.8 of IS 9573:2012)	A complete Hose assembly when subjected to internal hydraulic pressure equal to 5.0 MPa for 1 min, the change in the length shall be within the range of 12% of its original length.		Not Applicable	

Prepared By		Checked By	Page 4 of 4 + Drawing (47745)
			
UDIT KAUL		MAHENDAR PAL	
Asst. Manager		Sr. Manager	

